



**GRANULE MORVARID YAZD**  
COMPOUNDING & REPROCESSING of PLASTIC MATERIALS

**LDPE POLYETHYLENE**

**GM-FSH-T014(1)**

●Typical Application & Characteristics:

**GM-FSH-T014(1)** Is film grade compound based on the low density polyethylene (LDPE) .This grade offers easy process ability , very versatile of general-purpose films, shrink films, packaging films.Suitability for use in any application should be determined by appropriate performance testing.

**Product Description**

ITEM CODE	GM-FSH-T014 (1)
Grade	LDPE Polyethylene
Application	Blown Film
Color	Natural

**Typical Data**

TEST ITEM	UNIT	METHOD	VALUE
MFI (190 °C- 2.16kg)	gr/10min	ISO 1133	1±0.2
Density	gr/cm <sup>3</sup>	ISO 1183	0.920±0.005
Elongation at Break	%	ISO 527	≥700
Tensile Stress at Yield	MPA	ISO 527	11±2
Vicat Softening Point	°c	ASTM D-1525	93

**Remarks**

- Package: Plastic Bags 25 ± 0.1 Kg
- Storage: In manner to prevent of a direct exposure of sunlight or heat the storage area should be dry and preferably don't exceed 50 °C.GMY Co.do not give warranty to bad storage conditions lead to quality deterioration and inadequate product performance.
- Typical values: not to be construed as specification limits.
- Technical Disclaimer: The values reported in this technical data sheet are the results of tests carried out in accordance with standard test procedures in a laboratory environment. Actual properties may vary depending on batch and extrusion conditions. Therefore, these values should not be used for specification purposes.

Granule Morvarid Yazd Co. ISO: 9001-2015 certified  
Website: [www.gmy.co.ir](http://www.gmy.co.ir) E-mail: [sales@gmy.co.ir](mailto:sales@gmy.co.ir) [gmy.itd@gmail.com](mailto:gmy.itd@gmail.com)



**GRANULE MORVARID YAZD**  
COMPOUNDING & REPROCESSING of PLASTIC MATERIALS

**LDPE POLYETHYLENE**

**GM-FSH-T014(2)**

● Typical Application & Characteristics:

**GM-FSH-T014(2)** Is film grade compound based on the low density polyethylene (LDPE). This grade offers easy process ability, very versatile of general-purpose films, shrink films, packaging films. Suitability for use in any application should be determined by appropriate performance testing.

**Product Description**

ITEM CODE	GM-FSH-T014 (2)
Grade	LDPE Polyethylene
Application	Blown Film
Color	Natural

**Typical Data**

TEST ITEM	UNIT	METHOD	VALUE
MFI (190 °C- 2.16kg)	gr/10min	ISO 1133	1.6±0.2
Density	gr/cm <sup>3</sup>	ISO 1183	0.920±0.005
Elongation at Break	%	ISO 527	≥700
Tensile Stress at Yield	MPA	ISO 527	11±2
Vicat Softening Point	°c	ASTM D-1525	93

**Remarks**

- Package: Plastic Bags 25 ± 0.1 Kg
- Storage: In manner to prevent of a direct exposure of sunlight or heat the storage area should be dry and preferably don't exceed 50 °C. GMY Co.do not give warranty to bad storage conditions lead to quality deterioration and inadequate product performance.
- Typical values: not to be construed as specification limits.
- Technical Disclaimer: The values reported in this technical data sheet are the results of tests carried out in accordance with standard test procedures in a laboratory environment. Actual properties may vary depending on batch and extrusion conditions. Therefore, these values should not be used for specification purposes.